

RGO + CaCl2

CaCl2	#	ZP	stdev		
0.04	1	-2.7475	1.060475	-0.21532	0.083109
0.06	2	-1.3425	2.373996	-0.10521	0.18605
0.08	3	-0.91925	1.170242	-0.07204	0.091712
0.12	4	-0.40675	0.942437	-0.03188	0.073859
0.18	5	-0.28675	0.366791	-0.02247	0.028745
0.3	6	-0.223	0.254378	-0.01748	0.019936
0.4	7	-0.15295	0.282572	-0.01199	0.022145
0.6	8	-0.09065	0.357752	-0.0071	0.028037
1	9	-0.0242	0.359633	-0.0019	0.028184

RGO-Fe + CaCl2


CaCl2	#	ZP	stdev		
0.04	1	-2	-2.27	-0.15674	-0.1779
0.06	2	-1.17	-1.228	-0.09169	-0.09624
0.08	3	-0.719	-0.891	-0.05635	-0.06983
0.12	4	-0.305	-0.5198	-0.0239	-0.04074
0.18	5	-0.226	-0.2474	-0.01771	-0.01939
0.3	6	-0.171	-0.2046	-0.0134	-0.01603
0.4	7	-0.135	-0.1676	-0.01058	-0.01313
0.6	8	-0.0696	-0.14132	-0.00545	-0.01108
1	9	-0.0404	-0.1102	-0.00317	-0.00864


RGO-Ag + CaCl2

CaCl2	#	ZP	stdev		
0.04	1	-15.2625	0.834844	-1.19612	0.065427
0.06	2	-14.44	0.65803	-1.13166	0.05157
0.08	3	-13.4667	0.85049	-1.05538	0.066653
0.12	4	-10.4933	0.66493	-0.82236	0.052111
0.18	5	-8.15333	0.38004	-0.63898	0.029784
0.3	6	-7.2475	1.04729	-0.56799	0.082076
0.4	7	-5.68333	0.95924	-0.4454	0.075175
0.6	8	-3.3425	0.66339	-0.26195	0.05199
1	9	-1.15222	0.379656	-0.0903	0.029754

RGO-Fe-Ag + CaCl2

CaCl2	#	ZP	stdev		
0.04	1	-9.50	0.34641	-0.74451	0.027148
0.06	2	-8.38	1.85405	-0.65674	0.145302
0.08	3	-6.91	1.60982	-0.54154	0.126161
0.12	4	-6.08	1.447434	-0.47649	0.113435
0.18	5	-5.39	1.679042	-0.4223	0.131586
0.3	6	-4.05	1.796051	-0.3174	0.140756
0.4	7	-3.64	1.80578	-0.28511	0.141519
0.6	8	-1.44	0.537401	-0.11285	0.042116
1	9	-0.75	0.103078	-0.05858	0.008078





RGO-Ag + MgCl <sub>2</sub>						
MgCl <sub>2</sub>	#	ZP	stdev			
0.04	10	-10.7	0.8	-0.83856	0.062696	
0.06	11	-9.934	1.095345	-0.77853	0.085842	
0.08	12	-9.33	0.296985	-0.73119	0.023275	
0.12	13	-9.01	0.643377	-0.70611	0.050421	
0.18	14	-8.56333	0.636108	-0.67111	0.049852	
0.3	15	-7.465	0.685894	-0.58503	0.053753	
0.4	16	-6.08	0.652763	-0.47649	0.051157	
0.6	17	-3.94	0.765539	-0.30878	0.059995	
1	18	-1.2225	0.083815	-0.09581	0.006569	

RGO-Fe-Ag + MgCl <sub>2</sub>						
MgCl <sub>2</sub>	#	ZP	stdev			
0.04	10	-6.82	1.595082	-0.53448	0.125006	
0.06	11	-4.6433	0.92255	-0.3639	0.072301	
0.08	12	-3.17	1.27627	-0.24843	0.100021	
0.12	13	-1.715	0.28991	-0.1344	0.022721	
0.18	14	-1.51333	0.426654	-0.1186	0.033437	
0.3	15	-1.0885	1.076924	-0.08531	0.084398	
0.4	16	-0.93	0.188203	-0.07288	0.014749	
0.6	17	-0.901	0.111996	-0.07061	0.008777	
1	18	-0.53467	0.04817	-0.0419	0.003775	